

Sprej cink

Datum: februar 2015

Svojstva i oblasti upotrebe

Proizvod sprej cink je spreman za upotrebu. Štiti efikasno rezervoare, zavarene spojeve pilona, šipke, stolarske radove. Indikovana nakon operacija navoja, sečenja ili zavarivanja radi obnavljanja otpornosti na koroziju. Formirajte elastični film otporan na sve vremenske uslove koji se može ostaviti kao završna zaštita farbanom ili bilo kojom vrstom boje.

Ne oštećuje ozon.

Specifikacija pakovanja

Boca obložena folijom od 15 bara

Neto sadržaj	400 ml
Izgled	Boca koja sadrži tečnost pod pritiskom
Boja	Razne
Miris	Tipičan rastvarač
Gustina na 20°C	0.75 - 0.80 g/ml
Pritisak na 20°C	4.0 ± 0.5 bar
Pritisak na 50°C	8.0 ± 0.5 bar
Tačka zapaljivosti	Manje od 0° C
Viskozitet Ford Cup 4	11,3"
Preostali suvi cilindar	Od 15% do 22%
Grit to grindometro	Od 0 do 2 Micron
Sjaj	20 sjaja
Gustina 1 ruka	11 Micron
Gustina 3 ruke	22 Micron
Otpornost na temperaturu	100 - 120°C
Procenat cinka na suhu masu	1,35 %
Vreme sušenja:	
Otpornost na prašinu	10 minuta
Suvo na dodir	20 minuta
Potpuno suvo	24 sata

Može se prefarbati u bilo kom trenutku

Patentirana sigurnosna kapa zaštićena od dece

Referentni flaster u boji

Etiketiranje



Spray paint zinc

Date: February 2015

Properties and areas of use

Product spray paint zinc ready for use. Protects effectively tanks, pylons welded joints, bars, works of carpentry. Indicated after threading operations, cutting or welding to restore the corrosion resistance. Form a elastic film resistant to all weather conditions that can be left as a final protection painted or with any type of paint.

Does not damage the ozone.

Supply specifications

15 bar foil-coated can

Net content

400 ml

Appearance

Can containing pressurised liquid

Colour

Miscellaneous

Scent

Typical solvent

Density at 20°C

0.75 - 0.80 g/ml

Pressure at 20°C

4.0 ± 0.5 bar

Pressure at 50°C

8.0 ± 0.5 bar

Flammability point

less than 0° C

Viscosity Ford Cup 4

11,3"

Remaining dry cylinder

From 15% to 20%

Grit to grindometro

From 0 to 2 Micron

Gloss

20 Gloss

Thickness 1 hand

11 Micron

Thickness 3 hands

22 Micron

Temperature resistance

100 - 120°C

Percentage of zinc on the dry weight

1,35 %

Drying time:

Dust resistant

10 minutes

Dry to touch

20 minutes

Fully dry

24 hours

May be painted over at any time

Childproof patented safety cap

Colour reference patch

Labelling



code: SCIN
barcode: 8606017650324