

Sprej deko

Datum: decembar 2014

Svojstva i oblasti upotrebe

Taloženi metalni sloj daje predmetima prijatan izgled. Može ukasiti ramove za slike, ukrase, šolje, božićne predmete, samo za unutrašnju ugradnju. Efekat "listanja" može se oboriti trljanjem ili premazivanjem. Temperatura cilindra ne sme biti niža od 20-25°C. Boca od 400 ml pokriva površinu od 1,5 – 2 m², u zavisnosti od prirode nosača.

Specifikacija pakovanja

Boca obložena folijom od 15 bara

Neto sadržaj	400 ml
Izgled	Boca koja sadrži tečnost pod pritiskom
Boja	Razne
Miris	Tipičan rastvarač
Gustina na 20°C	0.75 – 0.80 g/ml
Pritisak na 20°C	4.0 ± 0.5 bar
Pritisak na 50°C	8.0 ± 0.5 bar
Tačka zapaljivosti	Manje od 0° C
Viskozitet Ford Cup 4	11"
Preostali suvi cilindar	Od 21% do 26.4%
Grit to grindometro	Od 8 do 10 Micron
Sjaj	/
Gustina 1 ruka	7-10 Micron
Gustina 3 ruke	22-30 Micron
Otpornost na temperaturu	110°C
Vreme sušenja:	
Otpornost na prašinu	10 minuta
Suvo na dodir	20 minuta
Potpuno suvo	24 sata

Može se prefarbati u bilo kom trenutku
 Patentirana sigurnosna kapa zaštićena od dece
 Referentni flaster u boji

Etiketiranje



šifra: SDE01
 barkod: 8606017650232

šifra: SDE02
 barkod: 8606017650249

šifra: SDE03
 barkod: 8606017650256

šifra: SDE04
 barkod: 8606017650263

šifra: SDE05
 barkod: 8606017650270

Paint spray deco

Date: December 2014

Properties and areas of use

The metal layer deposited gives objects a pleasant appearance. It can decorate picture frames, ornaments, cups, Christmas items, only for indoor installation. The effect of "leafing" can be shot down by rubbing or overcoating. The temperature of the cylinder must not be lower than 20-25 ° C. The 400 ml bottle covers an area of 1,5 - 2 m², depending on the nature of the support.

Supply specifications

15 bar foil-coated can	
Net content	400 ml
Appearance	Can containing pressurised liquid
Colour	Miscellaneous
Scent	Typical solvent
Density at 20°C	0.75 - 0.80 g/ml
Pressure at 20°C	4.0 ± 0.5 bar
Pressure at 50°C	8.0 ± 0.5 bar
Flammability point	less than 0° C
Viscosity Ford Cup 4	11"
Remaining dry cylinder	From 21% to 26.4%
Grit to grindometro	From 8 to 10 Micron
Gloss	/
Thickness 1 hand	7-10 Micron
Thickness 3 hands	22-30 Micron
Temperature resistance	110°C
Drying time:	
Dust resistant	10 minutes
Dry to touch	20 minutes
Fully dry	24 hours

May be painted over at any time
 Childproof patented safety cap
 Colour reference patch

Labelling



code: SDE01
 barcode: 8606017650232

code: SDE02
 barcode: 8606017650249

code: SDE03
 barcode: 8606017650256

code: SDE04
 barcode: 8606017650263

code: SDE05
 barcode: 8606017650270